

**AMENDMENT TO THE CLAIMS**

Claims 1-61 (canceled)

62. (new) A breathable, stretch-thinned elastic film comprising:  
a high performance styrene block copolymer elastomer;  
a low performance metallocene catalyzed polyolefin elastomer; and  
a plurality of filler particles;  
the film having a water vapor transmission rate of at least about 1000  
grams/m<sup>2</sup>/24 hours.

63. (new) A breathable, stretch-thinned elastic film comprising:  
a high performance styrene block copolymer elastomer;  
a low performance ethylene copolymer elastomer having a density less  
than 0.90 grams/cm<sup>3</sup>; and  
a plurality of filler particles;  
the film having a water vapor transmission rate of at least about 1000  
grams/m<sup>2</sup>/24 hours.

64. (new) The breathable, stretch-thinned film of Claim 62 or 63, wherein the styrene block copolymer elastomer comprises a tetrablock copolymer.

65. (new) The breathable, stretch-thinned film of Claim 62 or 63, wherein the styrene block copolymer elastomer comprises a diblock copolymer.

66. (new) The breathable, stretch-thinned film of Claim 62 or 63, wherein the low performance elastomer comprises an ethylene-alpha olefin copolymer in which the alpha-olefin is selected from the group consisting of 1-octene, 1-butene, 1-hexene and 4-methyl pentene.

67. (new) The breathable, stretch-thinned film of Claim 66, wherein the low performance elastomer has a density of about 0.86-0.89 grams/cm<sup>3</sup>.

68. (new) The breathable, stretch-thinned film of Claim 62 or 63, wherein the filler particles comprise inorganic filler particles.

69. (new) The breathable, stretch-thinned film of Claim 68, wherein the filler particles comprise calcium carbonate.

70. (new) The breathable, stretch-thinned film of Claim 62 or 63, comprising about 10-35% by weight of the low performance elastomer.

71. (new) The breathable, stretch-thinned film of Claim 62 or 63, comprising about 5-30% by weight of the high performance elastomer.

72. (new) The breathable, stretch-thinned film of Claim 62 or 63, comprising greater than about 50% by weight of the filler particles.

73. (new) The breathable, stretch-thinned film of Claim 62 or 63, comprising about 10-35% by weight of the low performance elastomer, about 5-30% of the high performance elastomer, and about 51-70% by weight of the filler particles.